



BICO STEEL

C1119

Free Machining Steel

C1119 Specifications

Specification	C1119
Thickness (Max. in.)	6
Chemical Composition	Unless a range is specified, individual values are maximums
Carbon	.17 / .23
Manganese	1.00 / 1.30
Phosphorus	.04
Sulfur	.20 / .33
Silicon	.30
Heat Treatment Required	-